

Falco Grey Oxide Primer

Product Description

Falco Grey Oxide Primer is based on Alkyd resin high performance anti rust primer. It is durable and enhances adhesion to the substrate.

Recommended Usage

To be used on interior and exterior surfaces such as steel and ferrous metals.

Technical Data

Color	Red	Red		
Finish	Smooth / Matt	Smooth / Matt		
Solid contents	52 % ± 2 by vol	52 % ± 2 by volume		
	Minimum	Maximum	Typical	
Wet film thickness (microns)	77	115	96	
Dry film thickness (microns)	40	60	50	
Theoretical spreading rate (m2/ltr.)	13	8.6	10	
Viscosity	9 – 12 poises at	9 – 12 poises at 25°C		
Specific gravity	1.45 <u>+</u> 0.05 gm/	1.45 <u>+</u> 0.05 gm/cm ³		
Drying time	Dry to touch (ho	Dry to touch (hours)		
	Dry to recoat (ho	Dry to recoat (hours)		
Thinner / Cleaning	Falco Thinner 10	Falco Thinner 1000		

<u>Hint</u>

Theoretical spreading rate is a value that depends on solid content and desired dry film thickness by the following equation:

Theoretical spreading rate =

10 x solid content by volume

DFT in microns

Application Data

Surface Preparation

The surface must be clean, dry and free from dust, oil, grease and any contaminations.

Tools

Brush, roller or spray.

Spray Data

Pressure at nozzle : 150 kg/cm2 (2100 PSI)

Nozzle tip (inches) : 0.015 - 0.017Spray Angle : $65^{\circ} - 80^{\circ}$

Filter : be sure that the filters are clean.

TDS 02-001 (Ver. 02) Page 1 of 3



Application Method

Apply one coat of Falco Grey Oxide Primer by brush, roller and spray thinned with Thinner 1000 (10-15% by volume).

Recommended paint system:

Falco Grey Oxide Primer
 Falco Lac Enamel
 1 coat
 2 coats

Note: paint system may be varying according to the substrate.

Packing size

- 1 liter, 1 US gallon and 5 US gallons steel cans (for local).
- 1 liter, 1 US gallon, 18 liters steel cans (for export).

Storage

- The product should be stored in a dry, cool place and away from direct sun light.
- Cans should be well closed, classified according to the base and to be arranged by a maximum 3 plastic cans/row and 5 steel cans/row.

Health and safety

• <u>Inhalation Risks:</u>

Vapor or mist can cause headache, nausea & irritation of the nose throat & lungs.

• Skin & Eye Contact:

Use good personal hygiene practices while working with this material. Dry contaminated clothing before reuse. For eye contact, flush with fresh water for at least 15 minutes. If irritation persists, get medical attention.

Skin Absorption : Not expected.

Ingestion Health Risks:

It may be harmful or fatal if swallowed. ingestion may cause nausea, vomiting & diarrhea. Consult a physician.

• <u>Health Hazards</u> : Acute & chronic (not expected).

• Emergency & First Aid Procedures:

Dermal : Clean with soap & water.
 Ingestion : Consult a physician.
 Inhalation : Remove to fresh air.

Fire & Fire Fighting Data

Flash Point : 38° C. Flammable limits : None.

Extinguishing media : Foam, Alcohol Foam, CO2 and dry chemical.

TDS 02-001 (Ver. 02) Page 2 of 3



Physical / Chemical Characteristics

Vapor Density : Heavier than air. Evaporation Rate : Slower than other.

Solubility in Water : Soluble.

Appearance/Odor : Liquid, Mild Odor

For more information please refer to the Material Safety Data Sheet.

TDS 02-001 (Ver. 02) Page **3** of **3**