

Falco Lac Enamel Super Star

Product Description

Falco Lac Enamel Super Star is based on high quality Alkyd resin enamel paint to provide maximum yellowing resistance and optimum hiding power with excellent weathering resistance.

Recommended Usage

To be used for interior and exterior surfaces such as concrete, plaster gypsum board wood and steel works.

Technical Data

Color	As per our color	As per our color card			
Finish	Smooth / Gloss,	Smooth / Gloss, Semi Gloss and Matt			
Solid contents	48 % ± 2 by vol	48 % ± 2 by volume			
	Minimum	Maximum	Typical		
Wet film thickness (microns)	83	125	104		
Dry film thickness (microns)	40	60	50		
Theoretical spreading rate (m2/ltr.)	12	8	9.6		
Viscosity	4 - 5 min. by for	4 - 5 min. by ford cup no. 4 @ 25°C			
Specific gravity	1.0 <u>+</u> 0.05 gm/c	1.0 <u>+</u> 0.05 gm/cm ³			
Drying time	Dry to touch (ho	ours)	3		
Drying time	Dry to recoat (hours)		6		
Thinner / Cleaning	Falco Thinner 10	Falco Thinner 1000			

<u>Hint</u>

Theoretical spreading rate is a value that depends on solid content and desired dry film thickness by the following equation:

Theoretical spreading rate =

10 x solid content by volume

DFT in microns

Application Data

Surface Preparation

The surface must be clean, dry and free from dust, oil, grease and any contaminations.

Tools

Brush, roller or spray.

Spray Data

Pressure at nozzle : 150 kg/cm2 (2100 PSI)

Nozzle tip (inches) : 0.013 - 0.021Spray Angle : $65^{\circ} - 80^{\circ}$

Filter : be sure that the filters are clean.

TDS 02-016 (Ver. 02) Page **1** of **3**



Application Method

Apply two coats of Falco Lac Enamel Super Star (top coat) by brush, roller and spray thinned with Thinner 1000 (10-15% by volume).

Recommended paint system for interior concrete:

•	Falco sealer Primer or Acrylic Emulsion Primer	1 coat
•	Falco Stucco Putty	2 coats
•	Falco Lac Enamel Super Star	2 coats

Recommended paint system for steel works:

•	Falco Red Oxide Primer	1 coat
•	Falco Lac Enamel Super Star	2 coats

Recommended paint system for wood works:

•	Falco Wood Primer	1 coat
•	Falco Stucco Putty (interior only)	2 coats
•	Falco Lac Enamel Super Star	2 coats

Note: paint system may be varying according to the substrate.

Packing size

- 1 liter, 1 US gallon and 5 US gallons steel cans (for local).
- 1 liter, 1 US gallon, 18 liters steel cans (for export).

Storage

- The product should be stored in a dry, cool place and away from direct sun light.
- Cans should be well closed, classified according to the base and to be arranged by a maximum 3 plastic cans/row and 5 steel cans/row.

Health and safety

Inhalation Risks:

Vapor or mist can cause headache, nausea & irritation of the nose throat & lungs.

Skin & Eye Contact:

Use good personal hygiene practices while working with this material. Dry contaminated clothing before reuse. For eye contact, flush with fresh water for at least 15 minutes. If irritation persists, get medical attention.

Skin Absorption : Not expected.

Ingestion Health Risks:

It may be harmful or fatal if swallowed. ingestion may cause nausea, vomiting & diarrhea. Consult a physician.

• <u>Health Hazards</u> : Acute & chronic (not expected).

TDS 02-016 (Ver. 02) Page 2 of 3



Emergency & First Aid Procedures:

Dermal : Clean with soap & water.
 Ingestion : Consult a physician.
 Inhalation : Remove to fresh air.

Fire & Fire Fighting Data

Flash Point : 38° C. Flammable limits : None.

Extinguishing media : Foam, Alcohol Foam, CO2 and dry chemical.

Physical / Chemical Characteristics

Vapor Density : Heavier than air. Evaporation Rate : Slower than other.

Solubility in Water : Soluble.

Appearance/Odor : Liquid, Mild Odor

For more information please refer to the Material Safety Data Sheet.

TDS 02-016 (Ver. 02) Page **3** of **3**